

## Pro Anti-Graffiti

Interlam™ Pro Anti-Graffiti is a 0.8 mil high performance PCTFE film with strong anti-graffiti characteristics and a pressure sensitive acrylic adhesive that is protected by a siliconized PE coated paper release liner. The film is flame resistant and provides a high degree of resistance to ultraviolet light, dirt and pollutants, and the gloss finish offers superb clarity, detail and color contrast. It wipes clean of virtually any spray paint and can be cleaned with most solvents and detergents without adverse effect. The premium adhesive creates a strong bond to UV inks as well as latex and other ink technologies.

- IDEAL FOR RETAIL ADVERTISING GRAPHICS, EVENT GRAPHICS OR DISPLAYS WHERE GRAFFITI MIGHT BE A POSSIBILITY, SUCH AS OUTDOOR BUS SHELTERS, TRAIN STATIONS AND KIOSKS
- CAN BE USED FOR CONSTRUCTION BARRICADE APPLICATIONS
- CAN BE USED FOR LONG-TERM EXTERIOR APPLICATIONS.

For more information, performance and warranty guidelines please contact your local Drytac office.

© 2018 Drytac Corporation. E&OE.  
All other trademarks are the property of their respective owners.

## TECHNICAL SPECIFICATION

### PRODUCT STRUCTURE

Film	High Performance PCTFE
Adhesive	Acrylic (Pressure Sensitive)
Release Liner	Siliconized PE Coated Paper

### PRODUCT CHARACTERISTIC

Film Thickness	0.8 mil	2 mil
Adhesive Layer	1.2 mil	
Film/Adhesive Ratio	0.8:1.2	
UV Protection Factor	UV resistant	
Outdoor Durability	5 Years	
Service Temperature Range	-13°F to 302°F (-25°C to 150°C)	
Shelf Life	1 year	
Storage Conditions	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity	

### PROCESS SETTINGS

Equipment Type & Temperature	Speed
Roller Laminator Room temperature to 104°F (40°C)	1 ft to 8 ft (0.3m to 2.5m) per minute
Press	Not recommended

**DRYTAC®**  
ADHESIVE SCIENCE



[www.digitalcolorink.com](http://www.digitalcolorink.com)  
877-616-8600  
Baltimore, MD | Charlotte, NC

**USA**  
5601 Eastport Boulevard,  
Richmond,  
Virginia, 23231,  
USA  
[customerservice@drytac.com](mailto:customerservice@drytac.com)  
Tel: +1 800.280.6013