



Printability:

(Eco)  
Solvent

Thickness (Total):

<b>200</b> μ	<b>7.9</b> mil	<b>235</b> gsm
-----------------	-------------------	-------------------

Latex



Thickness (Face):

<b>55</b> μ	<b>2.2</b> mil	<b>97</b> gsm
----------------	-------------------	------------------

UV



Adhesion:

Available widths:

<b>610</b> 24"	<b>762</b> 30"
-------------------	-------------------

<b>1372</b> 54"	<b>1524</b> 60"
--------------------	--------------------

## Metalik® Cut&Print

### Double-Sided Metallic Films - Removable

#### Applications

- Metallic Silver, Gold or Rose Gold double sided decorations
- Bright shiny lettering, logos and designs on shop-windows and glass
- Ideal for perfumeries, luxury boutiques, Christmas campaigns
- Perfect for temporary metallic surfaces
- Removable printed metallic POS decoration
- Combine print and CAD applications

Certified for  
HP Latex Inks

#### Benefits

- Same color effect on both sides, including very trendy rose gold
- Removable adhesive, perfect for wet-application
- Cuts perfectly, weeds easily
- Very smooth finish, close to mirror effect
- Corrosion free for outdoor durability
- Silver film up to 3 years outdoor use without fade, Gold & Rose Gold 1 year outdoor use

#### Post Printing Information for Latex & Solvent Inks:

As with all filmic media, this product must be allowed to "gas-out" after printing. This can be achieved by leaving the prints face up, ideally 24+ hours, to set, dry and harden. If unable to do this e.g. with a long print run: after printing the roll stand it vertically and loosely unwind the printed roll as much as possible, to allow air in and gases/solvents out.

#### Recommended Conditions:

Printroom	59°F - 85°F 15°C - 30°C	30% - 65% RH
Usage	-40°F - 176°F -40°C - 80°C	10% - 90% RH
Storage	50°F - 68°F 10°C - 20°C	20% - 50% RH


[www.digitalcolorink.com](http://www.digitalcolorink.com)
**877-616-8600**
**Baltimore, MD | Charlotte, NC**